



PercoTop®

CS582

Epoxy ZP High Build Coating

Features

- PercoTop® CS582 Epoxy ZP High Build Coating is a high-build 2K basic coating material based on epoxy resins, designed for the corrosion protection at steel constructions and industrial plants.
- Fast curing coating material.
- Application and curing is possible even with bad weather conditions.
- It is mechanical resistant and has an excellent adhesion.
- Certificate according to 687.02; 687.06 according to page 87 TL/TP-Kor-Stahlbauten.

Product

CS582 PercoTop® Epoxy ZP High Build Coating

Activator

CS571 PercoTop® Activator Special Epoxy

Thinner

CS561 PercoTop® Thinner Special Epoxy

Colour

- ca. RAL 1002 Sand yellow

Substrates

- Steel.
- Hot-dip galvanised steel according to DIN EN ISO 1461 and other non-ferrous metals.









For professional use only!

PercoTop[®]

CS582

Epoxy ZP High Build Coating

Application

	Application viscosity DIN 4 mm at 20°C (s)	Thinner (%)	Spray nozzle (mm)	Pressure (bar)	Number of coats
 Gravity feed  Suction feed (High pressure spraying)	According to the advice of the Technical Representative.				
 HVLP (Low pressure spraying)	According to the advice of the Technical Representative.				
 Airless Airmix	mixing viscosity	0-5%	0.33	2.0-3.5 atomizing pressure ca. 80-120 material	1-2
 Pressure Pot  Membrane Pump (High pressure spraying)	According to the advice of the Technical Representative.				
 Electrostatic	According to the advice of the Technical Representative.				
 Brush/roll	According to the advice of the Technical Representative. With thin-gauge steel fabrications or structures of complex configuration, the nominal prescribed filmbuild of 80 µm may be difficult to achieve, therefore additional application might be needed.				

PercoTop®

CS582

Epoxy ZP High Build Coating

Drying

Air drying temperature:	+5°C	+10°C	+20°C	+30°C
Dust dry	6 hours	3 hours	0.5 hours	20 min.
Dry to recoat	10 hours	6 hours	2 hours	1.5 hours
Dry to assemble	minimum of 10 hours / maximum of approx. 3 months			


Recoatability

Recoatable	PercoTop® Topcoats.
-------------------	---------------------

Product data

	Solids	Density	Theoretical coverage	Theoretical material consumption
	Weight (%) +/- 1	(kg/l) +/- 0.01	(at 80 µm) (m ² /kg)	(at 80 µm) (g/m ²)
Packaged	68	1.46	-	-
Ready for use (0% CS561)	68	1.37	4.7	213

Remarks


	<ul style="list-style-type: none"> Stir well before use.
	<ul style="list-style-type: none"> During application object temperature must reach at least 3°C above dew point.
Storage conditions	<ul style="list-style-type: none"> Refer to the label on the original can.



PercoTop[®]

CS582

Epoxy ZP High Build Coating

Note on safety:	
	This product is classified according to regulation (EC) 1272/2008 (CLP). Please consult the Safety Data Sheet. It is strongly recommended to use appropriate personal protection equipment during application.
	Observe the precautionary notices displayed on the container.

Information
<p>The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.</p> <p>This Technical Data Sheet supersedes all previous issues.</p>

<p>Copyright © 2014, Axalta Coating Systems, LLC and all affiliates. All rights reserved. The Axalta logo, Axalta[™], Axalta Coating Systems[™] and all products denoted with [™] or [®] are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta trademarks may not be used in connection with any product or service that is not an Axalta product or service.</p>
